

Cylindrical coordinates representation for valence-band and Kane Hamiltonians for wurtzite and zinc-blende heterostructures

Eduard Takhtamirov¹ and Roderick V. N. Melnik^{1,2}

¹⁾*M²NeT Laboratory, Wilfrid Laurier University, Waterloo, Ontario N2L 3C5, Canada^{a)}*

²⁾*BCAM, Bizkaia Technology Park, 48160 Derio, Spain^{b)}*

(Dated: 8 July 2011)

We derive closed-form expressions for 6×6 valence-band and 8×8 Kane Hamiltonians for wurtzite and zinc-blende semiconductor heterostructures in cylindrical coordinates, which provide a transparent and computationally efficient band formalism for low-dimensional semiconductor systems with the cylindrical symmetry. We use a specific combination of the Brillouin zone center Bloch functions as a new basis allowing to treat the envelope functions themselves as eigenstates of the operator of projection of total angular momentum on the symmetry axis, while the effective Hamiltonians parametrically depend on an eigenvalue of the operator. As an application, the developed method is used to map the ground and several excited hole states in an isolated wurtzite GaN quantum wire of the hexagonal cross-section to the states in an equivalent quantum wire of the circular cross-section.

PACS numbers: 73.21.-b

I. INTRODUCTION

Unique physical properties of artificial electron systems with two- and three-dimensional quantum confinement, realized in semiconductor quantum wires (QWs) and dots (QDs), have made them an object of extensive research, in particular in the last two decades¹. The current state of the art in the nanostructure technology and its steady improvement guarantees that QWs and QDs will inevitably become a basis for future generations of photonic and electronic devices^{2–5}, with QDs being viewed as one of the most promising candidates for use in solid-state quantum computation^{6–9}.

Despite the impressive progress in the application of atomistic approaches to actual nanostructures^{10–13}, the envelope function (EF) method still remains the most transparent means to study fundamental properties of electron states, and virtually the only efficient and flexible tool for optimization of nanostructure devices. A number of shortcomings of the original method^{14,15}, associated with the behavior of the wave functions at the heterointerfaces, have been proved to be not fatal when recipes of the method's modification have been developed and applied^{16–21}. Furthermore, for typical relatively large systems, with a small ratio of the number of heterointerface atoms to the number of atoms located inside homogeneous materials, the interface effects are usually weak, and an application of even the classic effective-mass approximation^{22–24} can be justified^{25,26}.

Already within the EF method, the calculation of electron states in QWs and QDs is still an arduous problem due to the necessity to solve a set of coupled partial differential equations, supplemented by the strain and elec-

tromechanical subtasks^{27–29}. Fortunately, for systems that are reasonably well approximated by those possessing cylindrical or spherical symmetry, one can reduce the number of independent variables and greatly facilitate the analysis. For a single-band equation, the transformation to cylindrical or spherical coordinates is a textbook task^{30,31}. Vahala and Sercel have presented a formalism, using the basis of Brillouin zone center Bloch functions as eigenstates of total angular momentum, allowing to integrate out the angular degree of freedom in the multiband Hamiltonians and leave only the radial, for spherically symmetric systems, or radial and axial, for cylindrically symmetric systems, variables^{32,33}. Their original method, developed for zinc-blende materials in the spherical band approximation^{34,35}, has since been used extensively, with an extension to wurtzite nanostructures³⁶.

Following that method, for a cylindrically symmetric nanostructure, for example, the effective Hamiltonian for each value of projection of total angular momentum on the symmetry axis should be obtained separately. As a result, the procedure has an infinite set of dissimilar Hamiltonians as an outcome, with such an intricacy reminding the formulation of the Heisenberg's matrix mechanics³⁰.

We develop an alternative approach to the multiband Hamiltonian for radially symmetric systems described by 6×6 valence-band or 8×8 Kane Hamiltonians for wurtzite and zinc-blende nanostructures. Considered only are systems that have the cylindrical symmetry so that the formalism can directly be applied to zinc-blende (truncated) conical QDs and cylindrical QWs, using the spherical band approximation^{34,35}, as well as to wurtzite cylindrically symmetric nanostructures grown along the [0001] direction. We expect that properties of corresponding pyramidal QDs can also be qualitatively modeled using the cylindrically symmetric shape approximation³⁷. Our resulting EF equations resem-

^{a)}Electronic mail: ed.takhtamirov@gmail.com

^{b)}Electronic mail: rmelnik@wlu.ca

ble the “single-band” Schrödinger equation expressed in cylindrical coordinates³¹, with the EFs themselves being eigenstates of the operator j_z of projection of angular momentum on the symmetry axis. For each specific case (wurtzite or zinc-blende, 6×6 or 8×8 model), we derive a unique effective Hamiltonian parametrically dependent on a single parameter that is an eigenvalue of j_z .

In Sec. II we deal with 6×6 Hamiltonians for the valence-band states. We start from the Hamiltonian in Cartesian coordinates for wurtzite (Subsection II A), make a cylindrical coordinates transformation (Subsection II B), include an external magnetic field (Subsection II C), derive the boundary conditions (BCs) to be imposed on the EFs on the symmetry axis (Subsection II D), and specify what changes in the results are to be made considering zinc-blende nanostructures (Subsection II E). In Sec. III we generalize the results of Sec. II for 8×8 Kane model, reviewing the Hamiltonian in Cartesian coordinates (Subsection III A) and presenting the resulting Hamiltonian in cylindrical coordinates (Subsection III B). As a simple application of the obtained results, in Sec. IV we study an isolated wurtzite GaN QW grown along the [0001] direction, both with the hexagonal cross-section in Cartesian coordinates and making the cylindrically symmetric shape approximation to use the Hamiltonian in cylindrical coordinates. We subsequently compare the spectra of hole states for these two cases. Conclusions are given in Sec. V.

II. HAMILTONIAN FOR VALENCE BAND

A. Hamiltonian for wurtzite in Cartesian coordinates

We start from the steady state Schrödinger equation in the effective-mass approximation^{22–24,38–41},

$$\mathbf{H}\mathbf{F} \equiv (\mathbf{H}^{(0)} + \mathbf{H}^{(\sigma)} + \mathbf{H}^{(k)} + \mathbf{H}^{(\varepsilon)})\mathbf{F} = E\mathbf{F}, \quad (1)$$

constructed using the orthogonal and normalized Brillouin zone center Bloch functions for the potential well material, which are written in the matrix form as $\mathbf{u} = (u_x \ u_y \ u_z)$. They can be chosen real. In Cartesian coordinates $\mathbf{r} = (x, y)$ and z , the functions $u_x = u_x(\mathbf{r}, z)$

and $u_y = u_y(\mathbf{r}, z)$ transform as the coordinates x and y belonging to the representation Γ_6 of the space group C_{6v} , while the function $u_z = u_z(\mathbf{r}, z)$ transforms as the coordinate z (along the c -axis of wurtzite) belonging to the representation Γ_1 . The EF matrix $\mathbf{F} = \mathbf{F}(\mathbf{r}, z)$ has three components: $\mathbf{F} = (F_x \ F_y \ F_z)^T$, where T stands for the transpose of a matrix or an operator, so that the total wave function $\Psi = \Psi(\mathbf{r}, z)$ is as follows:

$$\Psi = \sum_{j=x,y,z} u_j F_j = \mathbf{u}\mathbf{F}. \quad (2)$$

The basis functions $\mathbf{u}$ are spinless²², but each EF element F_j is a spinor having two components:

$$F_j = \begin{pmatrix} F_j^{(u)} \\ F_j^{(d)} \end{pmatrix}, \quad j = x, y, z. \quad (3)$$

The Hamiltonian $\mathbf{H}^{(0)}$ entering Eq. (1) represents the position-dependent potential energy of an electron:

$$\mathbf{H}^{(0)} = \begin{pmatrix} U_{v6} & 0 & 0 \\ 0 & U_{v6} & 0 \\ 0 & 0 & U_{v1} \end{pmatrix}, \quad (4)$$

where $U_{v6} = U_{v6}(\mathbf{r}, z)$ and $U_{v1} = U_{v1}(\mathbf{r}, z)$ are the position dependent edges of the valence bands Γ_6 and Γ_1 , respectively, which may include an external scalar potential.

The Hamiltonian $\mathbf{H}^{(\sigma)}$ entering Eq. (1) defines the spin-orbit interaction, which is taken into account in the first-order perturbation theory, neglecting small terms linear in the momentum operator^{38–40}:

$$\mathbf{H}^{(\sigma)} = \begin{pmatrix} 0 & -i\Delta_2\sigma_z & i\Delta_3\sigma_y \\ i\Delta_2\sigma_z & 0 & -i\Delta_3\sigma_x \\ -i\Delta_3\sigma_y & i\Delta_3\sigma_x & 0 \end{pmatrix}, \quad (5)$$

where σ_x , σ_y and σ_z are the Pauli matrices³¹:

$$\sigma_x = \begin{pmatrix} 0 & 1 \\ 1 & 0 \end{pmatrix}, \quad \sigma_y = \begin{pmatrix} 0 & -i \\ i & 0 \end{pmatrix}, \quad \sigma_z = \begin{pmatrix} 1 & 0 \\ 0 & -1 \end{pmatrix}, \quad (6)$$

and real $\Delta_2 = \Delta_2(\mathbf{r}, z)$ and $\Delta_3 = \Delta_3(\mathbf{r}, z)$ are the parameters of the valence-band spin-orbit splitting^{38–40}.

The Hamiltonian $\mathbf{H}^{(k)}$ of the Eq. (1) is:

$$\mathbf{H}^{(k)} = \begin{pmatrix} L_1 k_x^2 + M_1 k_y^2 + M_2 k_z^2 & N_1 k_x k_y & N_2 k_x k_z - N_3 k_x \\ N_1 k_x k_y & M_1 k_x^2 + L_1 k_y^2 + M_2 k_z^2 & N_2 k_y k_z - N_3 k_y \\ N_2 k_x k_z + N_3 k_x & N_2 k_y k_z + N_3 k_y & M_3 (k_x^2 + k_y^2) + L_2 k_z^2 \end{pmatrix}, \quad (7)$$

which presents the kinetic energy, where

$$\begin{aligned} L_1 &= \frac{\hbar^2}{2m_0} (A_2 + A_4 + A_5), & L_2 &= \frac{\hbar^2}{2m_0} A_1, \\ M_1 &= \frac{\hbar^2}{2m_0} (A_2 + A_4 - A_5), & N_1 &= \frac{\hbar^2}{2m_0} 2A_5, \end{aligned} \quad (8)$$

$$\begin{aligned} M_2 &= \frac{\hbar^2}{2m_0} (A_1 + A_3), & N_2 &= \frac{\hbar^2}{2m_0} \sqrt{2} A_6 \\ M_3 &= \frac{\hbar^2}{2m_0} A_2, & N_3 &= i\sqrt{2} A_7, \end{aligned} \quad (9)$$

with $A_1, A_2, \dots, A_7$ being real material parameters in conventional notations^{38,39,41}, m_0 is the free electron mass, and $\hbar k_j = -i\hbar\nabla_j$, where $j = x, y, z$, is the momentum operator. Not all parameters are independent:

$$L_1 - M_1 = N_1, \quad (10)$$

due to six-fold rotational symmetry of wurtzite³⁹, which actually leads to higher isotropic symmetry of the spectrum in bulk materials⁴⁰.

A common mistake is to treat the above parameters as position-dependent due to variation of the chemical com-

position of the heterostructure, while being limited with the second-order differential equations of the effective-mass approximation¹⁹. Here we assume them as the parameters of the potential well material.

To complete the definition of Eq. (1), the strain Hamiltonian $\mathbf{H}^{(\varepsilon)}$ has a structure resembling that of Eq. (7) because the tensor of deformation potential has the same transformation properties as the tensor of the reciprocal effective mass entering Eq. (7), both being governed by the lattice symmetry³⁸. We have:

$$\mathbf{H}^{(\varepsilon)} = \begin{pmatrix} l_1\varepsilon_{xx} + m_1\varepsilon_{yy} + m_2\varepsilon_{zz} & n_1\varepsilon_{xy} & n_2\varepsilon_{xz} \\ n_1\varepsilon_{xy} & m_1\varepsilon_{xx} + l_1\varepsilon_{yy} + m_2\varepsilon_{zz} & n_2\varepsilon_{yz} \\ n_2\varepsilon_{xz} & n_2\varepsilon_{yz} & m_3(\varepsilon_{xx} + \varepsilon_{yy}) + l_2\varepsilon_{zz} \end{pmatrix}, \quad (11)$$

where real parameters l_1, l_2, m_1, m_2, n_1 , and n_2 are expressed via conventional^{38,39,41} components of the deformation potential tensor as follows:

$$\begin{aligned} l_1 &= D_2 + D_4 + D_5, & m_1 &= D_2 + D_4 - D_5, \\ n_1 &= 2D_5, & l_2 &= D_1, & m_2 &= D_1 + D_3, \\ n_2 &= \sqrt{2}D_6, & m_3 &= D_2, \end{aligned} \quad (12)$$

and $\varepsilon = \varepsilon(\mathbf{r}, z)$ is the strain tensor in Cartesian coordinates⁴². Contrary to the effective-mass parameters, the deformation potentials can be treated as position-dependent because the strain directly modifies the potential energy of an electron, which is a dominant effect in view of the estimation of the terms entering the Hamiltonian⁴³. For heterostructures composed of related materials resulting in a weak position dependence of the band parameters, which is a requirement for the effective-mass method's applicability, the deformation potentials are also expected to have a weak position dependence. In this case parameters of the potential well material can be used for the whole structure.

Analogous to the identity of Eq. (10), an important relation takes place:

$$l_1 - m_1 = n_1, \quad (13)$$

which secures the cylindrically symmetric strain Hamiltonian for cylindrically symmetric strains. For a cylindrically symmetric system, $\mathbf{H}^{(0)}$, $\mathbf{H}^{(\sigma)}$ and ε depend on the absolute value of the vector $\mathbf{r}$.

B. Hamiltonian for wurtzite in cylindrical coordinates

To carry out a transformation from Cartesian (x, y, z) to cylindrical coordinates (r, ϕ, z) , with $x = r \cos \phi$ and $y = r \sin \phi$, it is important to transform all corresponding elements of the considered system. We thus introduce new “basis” functions $\tilde{\mathbf{u}} = (u_r, u_\phi, u_z)$ related to the func-

tions $\mathbf{u}$ as follows: $\mathbf{u} = \tilde{\mathbf{u}}\mathbf{S}$, where

$$\mathbf{S} = \begin{pmatrix} \cos \phi & \sin \phi & 0 \\ -\sin \phi & \cos \phi & 0 \\ 0 & 0 & 1 \end{pmatrix}, \quad (14)$$

which is a standard unitary matrix used to express Cartesian coordinates of a three-dimensional vector in terms of cylindrical ones. Explicit relations of the new functions u_r and u_ϕ to u_x and u_y read:

$$u_r = \frac{xu_x + yu_y}{\sqrt{x^2 + y^2}}, \quad u_\phi = \frac{xu_y - yu_x}{\sqrt{x^2 + y^2}}. \quad (15)$$

Note that u_r and u_ϕ are not Bloch functions, in particular they are not periodic.

The total wave function, see Eq. (2), is:

$$\Psi = \tilde{\mathbf{u}}\mathbf{S}\mathbf{F} \equiv \tilde{\mathbf{u}}\tilde{\mathbf{F}}, \quad (16)$$

where we have introduced the modified EF $\tilde{\mathbf{F}}$. The effective-mass Eq. (1) now reads:

$$\tilde{\mathbf{H}}\tilde{\mathbf{F}} = E\tilde{\mathbf{F}}, \quad (17)$$

where $\tilde{\mathbf{H}} = \mathbf{S}\mathbf{H}\mathbf{S}^{-1}$.

The potential energy Hamiltonian does not change:

$$\tilde{\mathbf{H}}^{(0)} = \mathbf{S}\mathbf{H}^{(0)}\mathbf{S}^{-1} = \mathbf{H}^{(0)}. \quad (18)$$

To transform the kinetic energy Hamiltonian presented by Eq. (7), we use Eq. (10) and the identities:

$$\begin{aligned} \nabla_x &= \cos \phi \nabla_r - \frac{\sin \phi}{r} \nabla_\phi, \\ \nabla_y &= \sin \phi \nabla_r + \frac{\cos \phi}{r} \nabla_\phi, \end{aligned} \quad (19)$$

where $\nabla_r = \partial/\partial r$ and $\nabla_\phi = \partial/\partial \phi$. Let us follow some algebra necessary to obtain the elements of the Hamiltonian $\tilde{\mathbf{H}}^{(k)} = \mathbf{S}\mathbf{H}^{(k)}\mathbf{S}^{-1}$. For example,

$$\begin{aligned}
\tilde{H}_{11}^{(k)} &= \cos \phi H_{11}^{(k)} \cos \phi + \cos \phi H_{12}^{(k)} \sin \phi + \sin \phi H_{21}^{(k)} \cos \phi + \sin \phi H_{22}^{(k)} \sin \phi \\
&= -L_1 (\cos \phi \nabla_x + \sin \phi \nabla_y) (\nabla_x \cos \phi + \nabla_y \sin \phi) - M_1 (\cos \phi \nabla_y - \sin \phi \nabla_x) (\nabla_y \cos \phi - \nabla_x \sin \phi) - M_2 \nabla_z^2 \\
&= -L_1 \left(\nabla_r^2 + \nabla_r \frac{1}{r} \right) - M_1 \frac{1}{r^2} \nabla_\phi^2 - M_2 \nabla_z^2,
\end{aligned} \tag{20}$$

$$\begin{aligned}
\tilde{H}_{12}^{(k)} &= -\cos \phi H_{11}^{(k)} \sin \phi + \cos \phi H_{12}^{(k)} \cos \phi - \sin \phi H_{21}^{(k)} \sin \phi + \sin \phi H_{22}^{(k)} \cos \phi \\
&= -L_1 (\cos \phi \nabla_x + \sin \phi \nabla_y) (\nabla_y \cos \phi - \nabla_x \sin \phi) - M_1 (\sin \phi \nabla_x - \cos \phi \nabla_y) (\nabla_x \cos \phi + \nabla_y \sin \phi) \\
&= -L_1 \nabla_r \frac{1}{r} \nabla_\phi + M_1 \left(\frac{1}{r} \nabla_r \nabla_\phi + \frac{1}{r^2} \nabla_\phi \right).
\end{aligned} \tag{21}$$

The rest elements are obtained analogously. The full matrix of the kinetic energy Hamiltonian $\tilde{\mathbf{H}}^{(k)}$ is:

$$\tilde{\mathbf{H}}^{(k)} = - \begin{pmatrix} L_1 \left[\nabla_r^2 + \nabla_r \frac{1}{r} \right] + M_1 \frac{\nabla_\phi^2}{r^2} + M_2 \nabla_z^2 & L_1 \nabla_r \frac{\nabla_\phi}{r} - M_1 \left[\frac{\nabla_\phi}{r} \nabla_r + \frac{\nabla_\phi}{r^2} \right] & N_2 \nabla_r \nabla_z - i N_3 \nabla_r \\ L_1 \left[\frac{\nabla_\phi}{r} \nabla_r + \frac{\nabla_\phi}{r^2} \right] - M_1 \nabla_r \frac{\nabla_\phi}{r} & M_1 \left[\nabla_r^2 + \nabla_r \frac{1}{r} \right] + L_1 \frac{\nabla_\phi^2}{r^2} + M_2 \nabla_z^2 & N_2 \frac{\nabla_\phi}{r} \nabla_z - i N_3 \frac{\nabla_\phi}{r} \\ N_2 \left[\nabla_r + \frac{1}{r} \right] \nabla_z + i N_3 \left[\nabla_r + \frac{1}{r} \right] & N_2 \frac{\nabla_\phi}{r} \nabla_z + i N_3 \frac{\nabla_\phi}{r} & M_3 \left[\nabla_r^2 + \frac{1}{r} \nabla_r + \frac{\nabla_\phi^2}{r^2} \right] + L_2 \nabla_z^2 \end{pmatrix}. \tag{22}$$

One should bear in mind that $\nabla_r^T = -(\nabla_r + r^{-1})$ to verify that the Hamiltonian of Eq. (22) is Hermitian (note also that the parameter N_3 is imaginary).

In a similar way as above, with the help of the identity

of Eq. (13), the strain Hamiltonian of Eq. (11) transforms into the Hamiltonian $\tilde{\mathbf{H}}^{(\varepsilon)} = \mathbf{S} \mathbf{H}^{(\varepsilon)} \mathbf{S}^{-1}$:

$$\tilde{\mathbf{H}}^{(\varepsilon)} = \begin{pmatrix} l_1 \varepsilon_{rr} + m_1 \varepsilon_{\phi\phi} + m_2 \varepsilon_{zz} & n_1 \varepsilon_{r\phi} & n_2 \varepsilon_{rz} \\ n_1 \varepsilon_{r\phi} & m_1 \varepsilon_{rr} + l_1 \varepsilon_{\phi\phi} + m_2 \varepsilon_{zz} & n_2 \varepsilon_{\phi z} \\ n_2 \varepsilon_{rz} & n_2 \varepsilon_{\phi z} & m_3 (\varepsilon_{rr} + \varepsilon_{\phi\phi}) + l_2 \varepsilon_{zz} \end{pmatrix}, \tag{23}$$

where $\varepsilon = \varepsilon(r, \phi, z)$ is now the strain tensor in cylindrical coordinates⁴². We have also used the following identities accompanying the coordinate change:

$$\begin{aligned}
\varepsilon_{xx} &= \varepsilon_{rr} \cos^2 \phi + \varepsilon_{\phi\phi} \sin^2 \phi - \varepsilon_{r\phi} \sin 2\phi, \\
\varepsilon_{yy} &= \varepsilon_{rr} \sin^2 \phi + \varepsilon_{\phi\phi} \cos^2 \phi + \varepsilon_{r\phi} \sin 2\phi, \\
\varepsilon_{xy} &= \frac{\varepsilon_{rr} - \varepsilon_{\phi\phi}}{2} \sin 2\phi + \varepsilon_{r\phi} \cos 2\phi, \\
\varepsilon_{xz} &= \varepsilon_{rz} \cos \phi - \varepsilon_{\phi z} \sin \phi, \\
\varepsilon_{yz} &= \varepsilon_{rz} \sin \phi + \varepsilon_{\phi z} \cos \phi,
\end{aligned} \tag{24}$$

which are in effect for any second-rank tensor. For cylindrically symmetric systems, the components of the strain tensor, expressed via the displacement vector $\mathbf{v} = (v_r, v_\phi, v_z)$, for which $v_\phi = 0$ and $\partial \mathbf{v} / \partial \phi = 0$, are⁴²:

$$\begin{aligned}
\varepsilon_{rr} &= \frac{\partial v_r}{\partial r}, \quad \varepsilon_{\phi\phi} = \frac{v_r}{r}, \quad \varepsilon_{zz} = \frac{\partial v_z}{\partial z}, \\
\varepsilon_{rz} &= \frac{1}{2} \left(\frac{\partial v_r}{\partial z} + \frac{\partial v_z}{\partial r} \right), \quad \varepsilon_{r\phi} = \varepsilon_{\phi z} = 0.
\end{aligned} \tag{25}$$

The spin-orbit interaction Hamiltonian of Eq. (5)

transforms into the Hamiltonian $\tilde{\mathbf{H}}^{(\sigma)} = \mathbf{S} \mathbf{H}^{(\sigma)} \mathbf{S}^{-1}$:

$$\tilde{\mathbf{H}}^{(\sigma)} = \begin{pmatrix} 0 & -i\Delta_2 \sigma_z & i\Delta_3 \sigma_\phi \\ i\Delta_2 \sigma_z & 0 & -i\Delta_3 \sigma_r \\ -i\Delta_3 \sigma_\phi & i\Delta_3 \sigma_r & 0 \end{pmatrix}, \tag{26}$$

where $\sigma_r = \sigma_x \exp(i\phi \sigma_z)$ and $\sigma_\phi = \sigma_y \exp(i\phi \sigma_z)$.

The spin-orbit Hamiltonian of Eq. (26) depends on ϕ and does not commute with the operator $-i\nabla_\phi$. To avoid this dependence, we note that

$$e^{i\frac{\phi}{2}\sigma_z} \sigma_r e^{-i\frac{\phi}{2}\sigma_z} = \sigma_x, \quad e^{i\frac{\phi}{2}\sigma_z} \sigma_\phi e^{-i\frac{\phi}{2}\sigma_z} = \sigma_y, \tag{27}$$

and then construct a unitary transformation of the EF:

$$\tilde{\mathbf{S}} \tilde{\mathbf{F}} = \tilde{\mathbf{F}}, \tag{28}$$

where

$$\tilde{\mathbf{S}} = \begin{pmatrix} e^{i\frac{\phi}{2}\sigma_z} & 0 & 0 \\ 0 & e^{i\frac{\phi}{2}\sigma_z} & 0 \\ 0 & 0 & e^{i\frac{\phi}{2}\sigma_z} \end{pmatrix}. \tag{29}$$

The effective-mass Eq. (17) now reads:

$$\tilde{\tilde{\mathbf{H}}}\tilde{\tilde{\mathbf{F}}} = E\tilde{\tilde{\mathbf{F}}}, \quad (30)$$

where $\tilde{\tilde{\mathbf{H}}} = \tilde{\mathbf{S}}\tilde{\mathbf{H}}\tilde{\mathbf{S}}^{-1}$.

The spin-orbit interaction Hamiltonian of Eq. (26) recovers its initial form given by Eq. (5):

$$\tilde{\tilde{\mathbf{H}}}^{(\sigma)} = \tilde{\mathbf{S}}\tilde{\mathbf{H}}^{(\sigma)}\tilde{\mathbf{S}}^{-1} = \mathbf{H}^{(\sigma)}. \quad (31)$$

The potential energy Hamiltonian of Eq. (18) and the strain Hamiltonian of Eq. (23) remain unchanged:

$$\tilde{\tilde{\mathbf{H}}}^{(0)} + \tilde{\tilde{\mathbf{H}}}^{(\epsilon)} = \tilde{\mathbf{S}} \left(\mathbf{H}^{(0)} + \mathbf{H}^{(\epsilon)} \right) \tilde{\mathbf{S}}^{-1} = \mathbf{H}^{(0)} + \mathbf{H}^{(\epsilon)}. \quad (32)$$

With the identity:

$$e^{i\frac{\phi}{2}\sigma_z} \nabla_\phi e^{-i\frac{\phi}{2}\sigma_z} = \nabla_\phi - \frac{i}{2}\sigma_z, \quad (33)$$

the kinetic energy Hamiltonian $\tilde{\tilde{\mathbf{H}}}^{(k)} = \tilde{\mathbf{S}}\tilde{\mathbf{H}}^{(k)}\tilde{\mathbf{S}}^{-1}$ still has the form given by Eq. (22) where the operator ∇_ϕ is replaced by the matrix operator:

$$\hat{\nabla}_\phi = \begin{pmatrix} \nabla_\phi - \frac{i}{2} & 0 \\ 0 & \nabla_\phi + \frac{i}{2} \end{pmatrix}. \quad (34)$$

We can express this fact by using the notations:

$$\tilde{\tilde{\mathbf{H}}}^{(k)} = \tilde{\mathbf{H}}^{(k)}(\nabla_\phi \rightarrow \hat{\nabla}_\phi). \quad (35)$$

For cylindrically symmetric systems, the Hamiltonian $\tilde{\tilde{\mathbf{H}}}$ now commutes with the operator of the z -projection of the angular momentum $j_z = -i\nabla_\phi$ (expressed in units of $\hbar$).

Note, that we could bypass the unitary transformation expressed by Eq. (28) but use the reciprocal transformation of the operator j_z :

$$J_z = e^{-i\frac{\phi}{2}\sigma_z} j_z e^{i\frac{\phi}{2}\sigma_z} = \frac{\nabla_\phi}{i} + \frac{1}{2}\sigma_z, \quad (36)$$

explicitly producing the operator of the z -projection of *total* angular momentum J_z that commutes with the Hamiltonian $\tilde{\tilde{\mathbf{H}}}$.

Being commuting operators, $\tilde{\tilde{\mathbf{H}}}$ and j_z have common eigenfunctions³¹, so that the EF $\tilde{\tilde{\mathbf{F}}} = \tilde{\tilde{\mathbf{F}}}(r, \phi, z)$ can be chosen in the following form:

$$\tilde{\tilde{\mathbf{F}}} = \frac{e^{im\phi}}{\sqrt{2\pi}} \mathbf{f}(r, z), \quad (37)$$

where m , being an eigenvalue of the operator of the z -component of electron's total angular momentum, should be half-integer: $m = \pm 1/2, \pm 3/2, \dots$. The function $\mathbf{f} = \mathbf{f}(r, z)$:

$$\mathbf{f} = \begin{pmatrix} f_1^{(u)} & f_1^{(d)} & f_2^{(u)} & f_2^{(d)} & f_3^{(u)} & f_3^{(d)} \end{pmatrix}^T, \quad (38)$$

satisfies the equation:

$$\left(\mathbf{H}^{(0)} + \mathbf{H}^{(\sigma)} + \tilde{\mathbf{H}}^{(\epsilon)} + \tilde{\tilde{\mathbf{H}}}^{(k)} \right) \mathbf{f} = E\mathbf{f}, \quad (39)$$

with $\mathbf{H}^{(0)}$, $\mathbf{H}^{(\sigma)}$ and $\tilde{\mathbf{H}}^{(\epsilon)}$ being given by Eqs. (4), (5) and (23), respectively, the latter should be supplemented by Eq. (25). Having m as a parameter, the kinetic energy Hamiltonian is:

$$\tilde{\tilde{\mathbf{H}}}^{(k)} = - \begin{pmatrix} L_1 \left[\nabla_r^2 + \nabla_r \frac{1}{r} \right] - M_1 \frac{\mathbf{m}^2}{r^2} + M_2 \nabla_z^2 & iL_1 \nabla_r \frac{\mathbf{m}}{r} - iM_1 \left[\frac{\mathbf{m}}{r} \nabla_r + \frac{\mathbf{m}}{r^2} \right] & N_2 \nabla_r \nabla_z - iN_3 \nabla_r \\ iL_1 \left[\frac{\mathbf{m}}{r} \nabla_r + \frac{\mathbf{m}}{r^2} \right] - iM_1 \nabla_r \frac{\mathbf{m}}{r} & M_1 \left[\nabla_r^2 + \nabla_r \frac{1}{r} \right] - L_1 \frac{\mathbf{m}^2}{r^2} + M_2 \nabla_z^2 & iN_2 \frac{\mathbf{m}}{r} \nabla_z + N_3 \frac{\mathbf{m}}{r} \\ N_2 \left[\nabla_r + \frac{1}{r} \right] \nabla_z + iN_3 \left[\nabla_r + \frac{1}{r} \right] & iN_2 \frac{\mathbf{m}}{r} \nabla_z - N_3 \frac{\mathbf{m}}{r} & M_3 \left[\nabla_r^2 + \frac{1}{r} \nabla_r - \frac{\mathbf{m}^2}{r^2} \right] + L_2 \nabla_z^2 \end{pmatrix}, \quad (40)$$

where the matrix $\mathbf{m}$ has a simple form:

$$\mathbf{m} = \begin{pmatrix} m - \frac{1}{2} & 0 \\ 0 & m + \frac{1}{2} \end{pmatrix}. \quad (41)$$

The total wave function Ψ and the EF $\tilde{\tilde{\mathbf{F}}}$ are related to each other via the conventional basis functions $\mathbf{u}$ or the modified ones $\tilde{\mathbf{u}}$ as follows:

$$\Psi = \mathbf{u}\mathbf{S}^{-1}\tilde{\mathbf{S}}^{-1}\tilde{\tilde{\mathbf{F}}} = \tilde{\mathbf{u}}\tilde{\mathbf{S}}^{-1}\tilde{\tilde{\mathbf{F}}}, \quad (42)$$

where the unitary matrices $\mathbf{S}$ and $\tilde{\mathbf{S}}$ are given by Eqs. (14) and (29), respectively. Since the functions u_r and u_ϕ

are not periodic, it is more convenient to use the old basis function $\mathbf{u}$, which are periodic and orthonormal, recovering the old EF $\mathbf{F}$:

$$\mathbf{F} = \mathbf{S}^{-1}\tilde{\mathbf{S}}^{-1}\tilde{\tilde{\mathbf{F}}}, \quad (43)$$

as soon as the effective-mass equation has been solved and the EF $\tilde{\tilde{\mathbf{F}}}$ has been found.

C. External magnetic field

An external magnetic field B_z , applied along the z -axis, does not break the cylindrical symmetry of the system if such exists. We use the symmetric gauge for the vector potential $\mathbf{A} = (A_x, A_y, A_z) = (-yB_z/2, xB_z/2, 0)$ in Cartesian coordinates, or $(A_r, A_\phi, A_z) = (0, rB_z/2, 0)$ in cylindrical coordinates. To include the magnetic field, we make the following substitution in the Hamiltonian of Eq. (7):

$$k_j \rightarrow K_j \equiv k_j + \frac{e}{\hbar c} A_j, \quad j = x, y, z, \quad (44)$$

where $-e < 0$ is the electron charge, and c is the speed of light in vacuum. All non-commutative products should be replaced by the symmetrized products²³:

$$K_x K_y \rightarrow \frac{1}{2} \{K_x, K_y\}_+ \equiv \frac{1}{2} (K_x K_y + K_y K_x). \quad (45)$$

In addition, the Hamiltonian $\mathbf{H}$ of Eq. (1) must include the effective Pauli term $\mathbf{H}^{(B)}$:

$$\mathbf{H}^{(B)} = \begin{pmatrix} \frac{g_0 \mu_B}{2} \sigma_z B_z & -\frac{ie}{2\hbar c} Q B_z & 0 \\ \frac{ie}{2\hbar c} Q B_z & \frac{g_0 \mu_B}{2} \sigma_z B_z & 0 \\ 0 & 0 & \frac{g_0 \mu_B}{2} \sigma_z B_z \end{pmatrix}, \quad (46)$$

The remaining arguments directly follow the ones for the case without magnetic field. Thus, the unitary transformation of Eq. (28) brings about the result of Eq. (35). The effective Pauli term of Eq. (46) remains invariant:

$$\tilde{\mathbf{H}}^{(B)} = \tilde{\mathbf{S}} \mathbf{H}^{(B)} \mathbf{S}^{-1} \tilde{\mathbf{S}}^{-1} = \mathbf{H}^{(B)}. \quad (52)$$

The resulting full Hamiltonian commutes with the operator $-i\nabla_\phi$, if the system is cylindrically symmetric. The EF has the form of Eq. (37), where the function $\mathbf{f}$ is

where $g_0 \approx 2$ is the free electron g -factor, μ_B is the Bohr magneton, and Q is a material specific parameter²³:

$$Q = \frac{\hbar^2}{m_0^2} \sum_{\gamma} \frac{p_{x\gamma}^{(x)} p_{\gamma y}^{(y)} - p_{x\gamma}^{(y)} p_{\gamma y}^{(x)}}{E_{v6} - E_{\gamma}}, \quad (47)$$

where E_{v6} is the energy of the valence Γ_6 state, with E_{γ} being the energy of γ band, for the potential well material, $p_{j'\gamma}^{(j)}$ are the matrix elements of the momentum operator between the Bloch zone-center functions u_{γ} and $u_{j'}$, where $j, j' = x, y$, that is $p_{j'\gamma}^{(j)} = \langle u_{j'} | \hbar k_j | u_{\gamma} \rangle$.

Let us compare Eq. (47) with a similar expression³⁹ for the material parameter N_1 :

$$N_1 = \frac{\hbar^2}{m_0^2} \sum_{\gamma} \frac{p_{x\gamma}^{(x)} p_{\gamma y}^{(y)} + p_{x\gamma}^{(y)} p_{\gamma y}^{(x)}}{E_{v6} - E_{\gamma}}, \quad (48)$$

and note that $p_{x\gamma}^{(y)} = 0$ for the nearest γ bands, which belong to the representation Γ_1 . This indicates that the approximation $Q \approx N_1$ may be satisfactory.

In cylindrical coordinates, for the Hamiltonian of Eq. (22) we symmetrize the products of the operators ∇_ϕ and ∇_r :

$$\nabla_\phi \nabla_r \rightarrow \frac{1}{2} \{ \nabla_\phi, \nabla_r \}_+, \quad (49)$$

and make the substitution:

$$\nabla_\phi \rightarrow \nabla_\phi + \frac{ie}{2\hbar c} B_z r^2, \quad (50)$$

so that, for example,

$$\tilde{H}_{12}^{(k)} = - \left\{ \nabla_\phi + \frac{ie}{2\hbar c} B_z r^2, \nabla_r \right\}_+ \frac{L_1}{2r} + \frac{M_1}{2r} \left\{ \nabla_\phi + \frac{ie}{2\hbar c} B_z r^2, \nabla_r \right\}_+ + \frac{M_1}{r^2} \left(\nabla_\phi + \frac{ie}{2\hbar c} B_z r^2 \right). \quad (51)$$

obtained by solving the following equation:

$$\left(\mathbf{H}^{(0)} + \mathbf{H}^{(\sigma)} + \tilde{\mathbf{H}}^{(\epsilon)} + \mathbf{H}^{(B)} + \tilde{\mathbf{H}}_m^{(k)} \right) \mathbf{f} = E \mathbf{f}, \quad (53)$$

where $\mathbf{H}^{(0)}$, $\mathbf{H}^{(\sigma)}$, $\tilde{\mathbf{H}}^{(\epsilon)}$, and $\mathbf{H}^{(B)}$ are given by Eqs. (4), (5), (23), and (46), respectively, while keeping in mind Eq. (25). The kinetic energy Hamiltonian $\tilde{\mathbf{H}}_m^{(k)}$ is presented by the matrix operator:

$$\begin{bmatrix} M_1 \frac{\hat{\mathbf{m}}^2}{r^2} - L_1 \left[\nabla_r^2 + \nabla_r \frac{1}{r} \right] - M_2 \nabla_z^2 & iM_1 \left[\frac{1}{2r} \{ \hat{\mathbf{m}}, \nabla_r \}_+ + \frac{\hat{\mathbf{m}}}{r^2} \right] - i \{ \hat{\mathbf{m}}, \nabla_r \}_+ + \frac{L_1}{2r} & -N_2 \nabla_r \nabla_z + iN_3 \nabla_r \\ i \{ \hat{\mathbf{m}}, \nabla_r \}_+ + \frac{M_1}{2r} - iL_1 \left[\frac{1}{2r} \{ \hat{\mathbf{m}}, \nabla_r \}_+ + \frac{\hat{\mathbf{m}}}{r^2} \right] & L_1 \frac{\hat{\mathbf{m}}^2}{r^2} - M_1 \left[\nabla_r^2 + \nabla_r \frac{1}{r} \right] - M_2 \nabla_z^2 & -iN_2 \frac{\hat{\mathbf{m}}}{r} \nabla_z - N_3 \frac{\hat{\mathbf{m}}}{r} \\ -N_2 \left[\nabla_r + \frac{1}{r} \right] \nabla_z - iN_3 \left[\nabla_r + \frac{1}{r} \right] & -iN_2 \frac{\hat{\mathbf{m}}}{r} \nabla_z + N_3 \frac{\hat{\mathbf{m}}}{r} & M_3 \left[\frac{\hat{\mathbf{m}}^2}{r^2} - \nabla_r^2 - \frac{1}{r} \nabla_r \right] - L_2 \nabla_z^2 \end{bmatrix}, \quad (54)$$

where the matrix operator $\hat{\mathbf{m}}$ is:

$$\hat{\mathbf{m}} = \begin{pmatrix} \frac{e}{2\hbar c} B_z r^2 + m - \frac{1}{2} & 0 \\ 0 & \frac{e}{2\hbar c} B_z r^2 + m + \frac{1}{2} \end{pmatrix}. \quad (55)$$

Also holds Eq. (42).

D. Structure of function $\mathbf{f}(r, z)$ at $r = 0$

We will determine the BCs imposed on the function $\mathbf{f}(r, z)$ entering Eq. (39) or (53) on the symmetry axis at $r = 0$. Having done this, to specify the eigenvalue problem, one should also complement Eqs. (39) and (53) with BCs at infinity, e.g., $\mathbf{f}(r, z)|_{r \rightarrow \infty} \rightarrow 0$ for discrete spectrum.

The BCs at $r = 0$ can easily be obtained from the continuity of the function $\mathbf{F}$, which satisfies Eq. (1), and its first partial derivatives $\nabla_j \mathbf{F}$ for $j = x, y$. We have the following explicit expressions connecting the old EF $\mathbf{F}$ and the modified one $\tilde{\mathbf{F}}$, obtained from Eqs. (37) and (43):

$$\begin{aligned} \sqrt{2\pi} F_x^{(u)} &= f_1^{(u)} e^{i\mu\phi} \cos \phi - f_2^{(u)} e^{i\mu\phi} \sin \phi, \\ \sqrt{2\pi} F_y^{(u)} &= f_1^{(u)} e^{i\mu\phi} \sin \phi + f_2^{(u)} e^{i\mu\phi} \cos \phi, \\ \sqrt{2\pi} F_z^{(u)} &= f_3^{(u)} e^{i\mu\phi}, \end{aligned} \quad (56)$$

for the upper elements of the envelope-function spinor components, where $\mu = m - 1/2$, and similar relations for the down elements, where the EF index (u) is substituted by (d) and $\nu = m + 1/2$ supersedes μ .

The continuity of the function $\mathbf{F}$ in particular on the symmetry axis means that

$$\mathbf{F}(\mathbf{r}, z)|_{x=r \cos \phi, y=r \sin \phi} \rightarrow \mathbf{F}(\mathbf{r}, z)|_{x=r, y=0}, \quad (57)$$

as $r \rightarrow 0$ for any angle ϕ . Then, using Eqs. (56) and (57), for the third component $f_3^{(u)}$ we have:

$$e^{i\mu\phi} f_3^{(u)}(r, z) \rightarrow f_3^{(u)}(r, z), \quad r \rightarrow 0, \quad \forall \phi, \quad (58)$$

which is an identity if $\mu = 0$, but definitely

$$f_3^{(u)}|_{r=0} = 0, \quad \mu \neq 0. \quad (59)$$

For the down element of the spinor, we obtain analogously:

$$f_3^{(d)}|_{r=0} = 0, \quad \nu \neq 0. \quad (60)$$

From the continuity condition of Eq. (57), using the first identity in Eq. (56), we have for any ϕ :

$$f_1^{(u)} e^{i\mu\phi} \cos \phi - f_2^{(u)} e^{i\mu\phi} \sin \phi \rightarrow f_1^{(u)}, \quad r \rightarrow 0, \quad (61)$$

which results in the following:

$$\begin{aligned} f_1^{(u)}|_{r=0} &= f_2^{(u)}|_{r=0} = 0, \quad |\mu| \neq 1, \\ f_2^{(u)}|_{r=0} &= i\mu f_1^{(u)}|_{r=0}, \quad |\mu| = 1. \end{aligned} \quad (62)$$

We will have the same result if we use the continuity of the function $F_y^{(u)}$. For the down elements it holds analogously:

$$\begin{aligned} f_1^{(d)}|_{r=0} &= f_2^{(d)}|_{r=0} = 0, \quad |\nu| \neq 1, \\ f_2^{(d)}|_{r=0} &= i\nu f_1^{(d)}|_{r=0}, \quad |\nu| = 1. \end{aligned} \quad (63)$$

To obtain the BCs imposed on the derivatives of the EF, we use the following continuity conditions for $r \rightarrow 0$ and any ϕ :

$$\nabla_j \mathbf{F}(\mathbf{r}, z)|_{x=r \cos \phi, y=r \sin \phi} \rightarrow \nabla_j \mathbf{F}(\mathbf{r}, z)|_{x=r, y=0}, \quad (64)$$

where $j = x, y$. For the element $f_3^{(u)}$, using its representation via $F_z^{(u)}$ in Eq. (56) as well as the conditions of Eq. (64) and the identities of Eq. (19), we have in particular:

$$\frac{\partial f_3^{(u)}}{\partial r} e^{i\mu\phi} \cos \phi - i\mu f_3^{(u)} \frac{\sin \phi}{r} e^{i\mu\phi} \rightarrow \frac{\partial f_3^{(u)}}{\partial r}, \quad (65)$$

as $r \rightarrow 0$ for any ϕ , from which we conclude that

$$\nabla_r f_3^{(u)}|_{r=0} = 0, \quad \mu = 0. \quad (66)$$

Analogously, for the down element:

$$\nabla_r f_3^{(d)}|_{r=0} = 0, \quad \nu = 0. \quad (67)$$

For the elements $f_1^{(u)}$ and $f_2^{(u)}$, we use the continuity conditions of Eq. (64), the first and the second identities of Eq. (56) along with the identities of Eq. (19). We obtain in particular that for any ϕ and $r \rightarrow 0$:

$$\begin{aligned} &\frac{\partial f_1^{(u)}}{\partial r} e^{i\mu\phi} \cos^2 \phi - \frac{\partial f_2^{(u)}}{\partial r} e^{i\mu\phi} \sin \phi \cos \phi \\ &+ \frac{f_1^{(u)}}{r} e^{i\mu\phi} (\sin^2 \phi - i\mu \sin \phi \cos \phi) \\ &+ \frac{f_2^{(u)}}{r} e^{i\mu\phi} (i\mu \sin^2 \phi + \sin \phi \cos \phi) \rightarrow \frac{\partial f_1^{(u)}}{\partial r}. \end{aligned} \quad (68)$$

For $|\mu| = 1$, using Eq. (62), we have:

$$\frac{\partial f_1^{(u)}}{\partial r} e^{i\mu\phi} \cos^2 \phi - \frac{\partial f_2^{(u)}}{\partial r} e^{i\mu\phi} \sin \phi \cos \phi \rightarrow \frac{\partial f_1^{(u)}}{\partial r}, \quad (69)$$

which is satisfied for any ϕ as $r \rightarrow 0$ if

$$\nabla_r f_1^{(u)}|_{r=0} = \nabla_r f_2^{(u)}|_{r=0} = 0, \quad |\mu| = 1. \quad (70)$$

For the down elements of the spinor components:

$$\nabla_r f_1^{(d)}|_{r=0} = \nabla_r f_2^{(d)}|_{r=0} = 0, \quad |\nu| = 1. \quad (71)$$

The conditions of Eqs. (59), (60), (62), (63), (66), (67), (70), and (71) constitute the complete set of the BCs that must be imposed on the function $\mathbf{f}(r, z)$ entering Eqs. (39) and (53) on the symmetry axis. They are summarized in Table I for convenience.

TABLE I. Boundary conditions imposed on elements of $\mathbf{f}(r, z)$ at $r = 0$ for different eigenvalues m of the operator of projection of total angular momentum on the symmetry axis.

m	1/2	-1/2	3/2	-3/2	other half-integers
$f_1^{(u)}$	0	—	—	0	0
$f_2^{(u)}$	0	$-if_1^{(u)}$	$if_1^{(u)}$	0	0
$f_3^{(u)}$	—	0	0	0	0
$\nabla_r f_1^{(u)}$	—	0	0	—	—
$\nabla_r f_2^{(u)}$	—	0	0	—	—
$\nabla_r f_3^{(u)}$	0	—	—	—	—
$f_1^{(d)}$	—	0	0	—	0
$f_2^{(d)}$	$if_1^{(d)}$	0	0	$-if_1^{(d)}$	0
$f_3^{(d)}$	0	—	0	0	0
$\nabla_r f_1^{(d)}$	0	—	—	0	—
$\nabla_r f_2^{(d)}$	0	—	—	0	—
$\nabla_r f_3^{(d)}$	—	0	—	—	—

E. Valence-band Hamiltonian for zinc-blende

The above results can be easily adapted to cylindrically symmetric nanostructures composed of zinc-blende semiconductors. The proper modifications are listed below.

The basis functions u_x , u_y and u_z now belong to the representation Γ_{15} of the space group T_d , so that in the potential energy Hamiltonian of Eq. (4) we put $U_{v6} = U_{v1}$, while in the spin-orbit interaction Hamiltonians of Eqs. (5) and (26) we have $\Delta_2 = \Delta_3 = \Delta/3$, where Δ is the valence-band spin-orbit splitting in cubic materials²².

For the parameters entering the kinetic energy Hamiltonians of Eqs. (7), (22), (40), and (54) we have the following identities:

$$L_1 = L_2, \quad M_1 = M_2 = M_3, \quad N_1 = N_2, \quad N_3 = 0. \quad (72)$$

Three parameters L_1 , M_1 , and N_1 are expressed via the Luttinger parameters γ_1 , γ_2 , and γ_3 as follows²³:

$$\begin{aligned} \frac{\gamma_1}{2m_0} &= -\frac{1}{3}(L_1 + 2M_1), \quad \frac{\gamma_2}{2m_0} = -\frac{1}{6}(L_1 - M_1), \\ \frac{\gamma_3}{2m_0} &= -\frac{1}{6}N_1. \end{aligned} \quad (73)$$

Equation (10) is not an identity for zinc-blende, equivalent to $\gamma_2 = \gamma_3$, but the recipe for the spherical band approximation^{34,35}.

Analogously, in the strain Hamiltonians of Eqs. (11) and (23) we have:

$$l_1 = l_2, \quad m_1 = m_2 = m_3, \quad n_1 = n_2. \quad (74)$$

The valence-band deformation potentials a , b , and d are expressed via these parameters as follows^{48,49}:

$$a = -\frac{1}{3}(l_1 + 2m_1), \quad b = \frac{1}{3}(l_1 - m_1), \quad d = \frac{1}{\sqrt{3}}n_1. \quad (75)$$

The validity of Eq. (13) is not hence guaranteed, equivalent to

$$d = \sqrt{3}b. \quad (76)$$

Whether Eq. (76), which expresses the spherical deformation potential approximation, is acceptable or not should be analyzed for each specific case. In Table II we present a comparison of the deformation potentials $\sqrt{3}b$ and d along with a comparison of the Luttinger parameters γ_2 and γ_3 . It can be seen that the spherical deformation potential approximation may be as good as the spherical band approximation, while there exist materials for which one or both of these approximations are poor.

TABLE II. Comparison of the valence-band deformation potentials $\sqrt{3}b$ and d , and the Luttinger parameters γ_2 and γ_3 for some zinc-blende semiconductors. The material parameters are taken from Ref. 50.

Parameter	GaAs	AlAs	InAs	GaP	AlP	InP	GaN	AlN	InN
b (eV)	-2.0	-2.3	-1.8	-1.6	-1.5	-2.0	-2.2	-1.9	-1.2
d (eV)	-4.8	-3.4	-3.6	-4.6	-4.6	-5.0	-3.4	-10	-9.3
γ_2	2.06	0.82	8.5	0.49	0.71	1.60	0.75	0.47	1.26
γ_3	2.93	1.42	9.2	2.93	1.23	2.10	1.10	0.85	1.63
$\sqrt{3}b/d$	0.72	1.17	0.87	0.60	0.56	0.69	1.12	0.33	0.22
γ_2/γ_3	0.70	0.58	0.92	0.17	0.58	0.76	0.68	0.55	0.77

III. HAMILTONIAN FOR KANE MODEL

A. Cartesian coordinates

The Kane model⁴⁴ takes into account the direct interaction of the valence and conduction bands exactly while the interaction mediated by remote bands is treated to the second order within the Löwdin perturbation scheme^{38,45}. The model is used for narrow bandgap systems when the energies of interest (e.g. band offsets) are comparable with the bandgap, but other bands can still be treated as remote. There exists a controversy regarding the model for wurtzite^{46,47}, though concerning minor contributions yet currently lacking experimental values for the corresponding material parameters. Furthermore, for heterostructures composed of wurtzite type semiconductors the potential of variation of the chemical composition acquires an “unusual” non-diagonal contribution due to the fact that the conduction and one of the valence band edge Bloch functions belong to the same representation Γ_1 of the space group C_{6v} . We highlight all these points below.

The steady state EF equation of the Kane model can be written as follows:

$$\mathbf{H}'\mathbf{F}' = E\mathbf{F}', \quad (77)$$

where

$$\mathbf{H}' = \begin{pmatrix} H_c & \mathbf{H}_{cv} \\ \mathbf{H}_{cv}^\dagger & \mathbf{H}_v \end{pmatrix}, \quad \mathbf{F}' = \begin{pmatrix} F_c \\ \mathbf{F}_v \end{pmatrix}, \quad (78)$$

and $\mathbf{H}_{cv}^\dagger$ is the Hermitian conjugate of $\mathbf{H}_{cv}$. The conduction- and the valence-band EFs are $F_c = F_c(\mathbf{r}, z)$ and $\mathbf{F}_v = \mathbf{F}_v(\mathbf{r}, z)$, respectively, the latter has the components F_x , F_y , and F_z . As in Eq. (2), the total wave function Ψ is:

$$\Psi = \sum_{j=c,x,y,z} u_j F_j = \mathbf{u}' \mathbf{F}', \quad (79)$$

which explicitly depends also on the conduction-band zone-center Bloch function $u_c = u_c(\mathbf{r}, z)$, so that $\mathbf{u}' = (u_c \ u_x \ u_y \ u_z)$ and $\mathbf{F}' = (F_c \ F_x \ F_y \ F_z)^T$. As above, the basis functions $\mathbf{u}'$, which can be chosen real, are spinless while each EF element F_j is a spinor:

$$F_j = \begin{pmatrix} F_j^{(u)} \\ F_j^{(d)} \end{pmatrix}, \quad j = c, x, y, z. \quad (80)$$

We now proceed to the description of the matrix Hamiltonian $\mathbf{H}'$ of Eq. (78). The intra-conduction band block is:

$$H_c = A'_1 k_z^2 + A'_2 (k_x^2 + k_y^2) + U_c + a_1 \varepsilon_{zz} + a_2 (\varepsilon_{xx} + \varepsilon_{yy}), \quad (81)$$

where $U_c = U_c(\mathbf{r}, z)$ is the position dependent edge of the conduction band Γ_1 , which also includes an external scalar potential if it is present, a_1 and a_2 are the deformation potentials for the conduction band. The parameters A'_1 and A'_2 are expressed via the components $1/m_1$ and $1/m_2$ of the tensor of the reciprocal effective mass for the conduction band in the single-band approximation and the Kane parameters (can be chosen real) $P_1 = -i\hbar \langle u_c | \hbar k_z | u_z \rangle / m_0$ and $P_2 = -i\hbar \langle u_c | \hbar k_x | u_x \rangle / m_0$ as follows:

$$A'_1 = \frac{\hbar^2}{2m_1} - \frac{P_1^2}{E_c - E_{v1}}, \quad (82)$$

$$A'_2 = \frac{\hbar^2}{2m_2} - \frac{P_2^2}{E_c - E_{v6}}, \quad (83)$$

where E_c and E_{v1} are the energies of the conduction Γ_1 and valence Γ_1 states, respectively.

The intra-valence band block is:

$$\mathbf{H}_v = \mathbf{H}^{(0)} + \mathbf{H}^{(\sigma)} + \mathbf{H}^{(\varepsilon)} + \mathbf{H}^{(k)}, \quad (84)$$

where $\mathbf{H}^{(0)}$, $\mathbf{H}^{(\sigma)}$ and $\mathbf{H}^{(\varepsilon)}$ are given by Eqs. (4), (5) and (11), respectively. The form of Eq. (7) is also preserved for the kinetic energy Hamiltonian $\mathbf{H}^{(k)}$ while some of the parameters are adjusted to exclude contributions from the interaction with the conduction band:

$$\mathbf{H}^{(k)} = \begin{pmatrix} L'_1 k_x^2 + M_1 k_y^2 + M_2 k_z^2 & N'_1 k_x k_y & N'_2 k_x k_z - N_3 k_x \\ N'_1 k_x k_y & M_1 k_x^2 + L'_1 k_y^2 + M_2 k_z^2 & N'_2 k_y k_z - N_3 k_y \\ N'_2 k_x k_z + N_3 k_x & N'_2 k_y k_z + N_3 k_y & M_3 (k_x^2 + k_y^2) + L'_2 k_z^2 \end{pmatrix}, \quad (85)$$

where

$$\begin{aligned} L'_1 &= L_1 + \frac{P_2^2}{E_c - E_{v6}}, & L'_2 &= L_2 + \frac{P_1^2}{E_c - E_{v1}}, \\ N'_1 &= N_1 + \frac{P_2^2}{E_c - E_{v6}}, \\ N'_2 &= N_2 + \frac{P_1 P_2 (2E_c - E_{v1} - E_{v6})}{2(E_c - E_{v6})(E_c - E_{v1})}. \end{aligned} \quad (86)$$

For the interband block $\mathbf{H}_{cv}$ of the Hamiltonian of Eq. (78) we have:

$$\mathbf{H}_{cv} = \begin{pmatrix} H_{cv1} & H_{cv2} & H_{cv3} \end{pmatrix}, \quad (87)$$

where

$$H_{cv1} = iP_2 k_x + B_2 k_x k_z + b_2 \varepsilon_{xz}, \quad (88)$$

$$H_{cv2} = iP_2 k_y + B_2 k_y k_z + b_2 \varepsilon_{yz}, \quad (89)$$

$$\begin{aligned} H_{cv3} &= iP_1 k_z + B_1 k_z^2 + B_3 (k_x^2 + k_y^2) \\ &\quad + b_1 \varepsilon_{zz} + b_3 (\varepsilon_{xx} + \varepsilon_{yy}) + U_{cz}, \end{aligned} \quad (90)$$

where we have neglected strain-induced $\mathbf{k} \cdot \mathbf{p}$ -interaction terms^{38,48}, proportional to ε , which are very small because for typical semiconductor heterostructures $\varepsilon \sim 10^{-2}$. The parameters entering Eqs. (88)-(90) have the following meanings: $b_1 = \langle u_c | D^{zz} | u_z \rangle$, $b_2 = \langle u_c | D^{xz} | u_x \rangle$ and $b_3 = \langle u_c | D^{xx} | u_z \rangle$ are the interband matrix elements of the deformation potential tensor $\mathbf{D}^{38,48}$. For the parameters B_1 , B_2 and B_3 we have:

$$B_1 = \frac{\hbar^2}{2m_0^2} \sum_{\gamma} \left(\frac{1}{E_{v1} - E_{\gamma}} + \frac{1}{E_c - E_{\gamma}} \right) p_{c\gamma}^{(z)} p_{\gamma z}^{(z)}, \quad (91)$$

$$\begin{aligned} B_2 &= \frac{\hbar^2}{2m_0^2} \sum_{\gamma} \left(\frac{1}{E_{v1} - E_{\gamma}} + \frac{1}{E_c - E_{\gamma}} \right) \\ &\quad \times \left(p_{c\gamma}^{(x)} p_{\gamma z}^{(z)} + p_{c\gamma}^{(z)} p_{\gamma z}^{(x)} \right), \end{aligned} \quad (92)$$

$$B_3 = \frac{\hbar^2}{2m_0^2} \sum_{\gamma} \left(\frac{1}{E_{v1} - E_{\gamma}} + \frac{1}{E_c - E_{\gamma}} \right) p_{c\gamma}^{(x)} p_{\gamma z}^{(x)}. \quad (93)$$

The Kane Hamiltonian given in Ref. 46, Eq. (A4), is not applicable to wurtzite. The terms of the conduction-valence interband interaction mediated by remote bands, which are proportional to the parameters B_1 and B_2 there, are proper not for wurtzite but zinc-blende materials⁴⁸, after elimination of a misprint in the elements $(H_2)_{14}$ and $(H_2)_{41}$, and putting $B_1 = B_2$. On the other hand, the Kane Hamiltonian presented in Ref. 47, Eq. (4), is lacking the term proportional to B_1 in our Eq. (90).

The interband potential $U_{cz} = U_{cz}(\mathbf{r}, z)$ entering Eq. (90) can be associated with the difference in the Bloch functions for the semiconductors composing the heterostructure. We can use $U_{cz} = 0$ for the space region of the reference (potential well) semiconductor, which has the periodic lattice potential $U_1 = U_1(\mathbf{r}, z)$, while for the space region of the barrier material with the lattice potential $U_2 = U_2(\mathbf{r}, z)$ we have^{19,24} $U_{cz} = \langle u_c | U_2 - U_1 | u_z \rangle$. This step-like contribution exists even for heterostructures with graded composition, so that this interband offset can be estimated knowing only bulk parameters of the semiconductors. It will be done elsewhere.

If we adopt the cubic approximation^{38–40}, which imposes the zinc-blende crystal symmetry on potentials of the wurtzite semiconductors, all parameters corresponding to the controversial terms as well as the interband offset will turn to zero:

$$B_1 = B_2 = B_3 = b_1 = b_2 = b_3 = U_{cz} = 0. \quad (94)$$

Also, $N_3 = \hbar p_{zx}^{(x)}/m_0 = 0$, and $E_{v1} = E_{v6}$ in the denominators of Eqs. (82), (83) and (86). Interesting, that contributions of similar origin in zinc-blende materials⁴⁸, which disappear for wurtzite, can hence be treated as small on reciprocal grounds, rather than via invoking an affinity of the zinc-blende and the diamond lattices. In what follows we use the approximations given by Eq. (94).

For a zinc-blende nanostructure, we use the relations given in Subsection II E, along with $a_1 = a_2$ in Eq. (81), $m_1 = m_2$, $P_1 = P_2$, and $E_{v1} = E_{v6}$ in Eqs. (82), (83), (88), (89), and (90).

B. Cylindrical coordinates

The procedure of transformation of the Kane Hamiltonian to cylindrical coordinates closely follows the one for the valence band case. We accordingly introduce the zone-center functions $\tilde{\mathbf{u}}' = (u_c \ u_r \ u_{\phi} \ u_z)$ related to the functions $\mathbf{u}'$ as follows: $\mathbf{u}' = \tilde{\mathbf{u}}' \mathbf{S}'$, where the unitary

matrix

$$\mathbf{S}' = \begin{pmatrix} 1 & \mathbf{0} \\ \mathbf{0} & \mathbf{S} \end{pmatrix} \equiv \begin{pmatrix} 1 & 0 & 0 & 0 \\ 0 & \cos \phi & \sin \phi & 0 \\ 0 & -\sin \phi & \cos \phi & 0 \\ 0 & 0 & 0 & 1 \end{pmatrix} \quad (95)$$

plays the role of the matrix $\mathbf{S}$ for the valence-band case, see Eq. (14). To avoid the ϕ -dependence in the spin-orbit Hamiltonian after the unitary transformation realized with the matrix $\mathbf{S}'$, we also use the unitary transformation defined by the unitary matrix $\tilde{\mathbf{S}}'$, with the counterpart of Eq. (29) from the valence band case:

$$\tilde{\mathbf{S}}' = \begin{pmatrix} e^{i\frac{\phi}{2}\sigma_z} & 0 & 0 & 0 \\ 0 & e^{i\frac{\phi}{2}\sigma_z} & 0 & 0 \\ 0 & 0 & e^{i\frac{\phi}{2}\sigma_z} & 0 \\ 0 & 0 & 0 & e^{i\frac{\phi}{2}\sigma_z} \end{pmatrix}. \quad (96)$$

The resulting doubly transformed Hamiltonian $\mathbf{H}'$ of Eq. (77) is:

$$\tilde{\mathbf{H}}' = \tilde{\mathbf{S}}' \mathbf{S}' \mathbf{H}' \mathbf{S}'^{-1} \tilde{\mathbf{S}}'^{-1} = \begin{pmatrix} \tilde{\tilde{H}}_c & \tilde{\tilde{H}}_{cv} \\ \tilde{\tilde{H}}_{cv}^{\dagger} & \tilde{\tilde{H}}_v \end{pmatrix}, \quad (97)$$

where

$$\begin{aligned} \tilde{\tilde{H}}_c = & -A'_1 \nabla_z^2 - A'_2 \left[\nabla_r^2 + \frac{1}{r} \nabla_r + \frac{1}{r^2} \hat{\nabla}_{\phi}^2 \right] \\ & + U_c + a_1 \varepsilon_{zz} + a_2 (\varepsilon_{rr} + \varepsilon_{\phi\phi}), \end{aligned} \quad (98)$$

$$\tilde{\tilde{H}}_{cv} = \begin{pmatrix} \tilde{\tilde{H}}_{cv1} & \tilde{\tilde{H}}_{cv2} & \tilde{\tilde{H}}_{cv3} \end{pmatrix}, \quad (99)$$

with

$$\tilde{\tilde{H}}_{cv1} = P_2 \left(\nabla_r + \frac{1}{r} \right), \quad (100)$$

$$\tilde{\tilde{H}}_{cv2} = P_2 \frac{1}{r} \hat{\nabla}_{\phi}, \quad \tilde{\tilde{H}}_{cv3} = P_1 \nabla_z. \quad (101)$$

Note that

$$\tilde{\tilde{H}}_{cv1}^{\dagger} = -P_2 \nabla_r, \quad (102)$$

while

$$\tilde{\tilde{H}}_{cv2}^{\dagger} = -P_2 \frac{1}{r} \hat{\nabla}_{\phi}, \quad \tilde{\tilde{H}}_{cv3}^{\dagger} = -P_1 \nabla_z. \quad (103)$$

For the intra-valence band block $\tilde{\tilde{H}}_v$ we have:

$$\tilde{\tilde{H}}_v = \mathbf{H}^{(0)} + \mathbf{H}^{(\sigma)} + \mathbf{H}^{(\varepsilon)} + \tilde{\tilde{H}}'^{(k)}, \quad (104)$$

where $\mathbf{H}^{(0)}$, $\mathbf{H}^{(\sigma)}$ and $\mathbf{H}^{(\varepsilon)}$ are given by Eqs. (4), (5) and (23), respectively, bearing in mind Eq. (25). For the

kinetic energy part $\tilde{\mathbf{H}}^{(k)}$ we use the matrix Hamiltonian of Eq. (22) with the substitution $\nabla_\phi \rightarrow \hat{\nabla}_\phi$, see Eq. (35), along with the substitutions $L_1 \rightarrow L'_1$, $L_2 \rightarrow L'_2$, $N_1 \rightarrow N'_1$ and $N_2 \rightarrow N'_2$, see Eq. (86).

The external magnetic field B_z is treated analogously to the valence-band case, via the substitution given by Eqs. (49) and (50), and an inclusion of the following Pauli term $\mathbf{H}^{(B)}$ in the Hamiltonian $\tilde{\mathbf{H}}'$:

$$\mathbf{H}^{(B)} = \begin{pmatrix} \frac{g_0 \mu_B}{2} \sigma_z B_z & 0 & 0 & 0 \\ 0 & \frac{g_0 \mu_B}{2} \sigma_z B_z & -\frac{ie}{2\hbar c} Q B_z & 0 \\ 0 & \frac{ie}{2\hbar c} Q B_z & \frac{g_0 \mu_B}{2} \sigma_z B_z & 0 \\ 0 & 0 & 0 & \frac{g_0 \mu_B}{2} \sigma_z B_z \end{pmatrix}, \quad (105)$$

which is invariant under the transformations realized with the matrices $\mathbf{S}'$ and $\tilde{\mathbf{S}}'$.

For a cylindrically symmetric system, the Hamiltonian $\tilde{\mathbf{H}}'$ commutes with the operator $-i\nabla_\phi$. The EF $\tilde{\mathbf{F}}' = \tilde{\mathbf{S}}' \mathbf{S}' \mathbf{F}'$, which satisfies the equation:

$$\tilde{\mathbf{H}}' \tilde{\mathbf{F}}' = E \tilde{\mathbf{F}}', \quad (106)$$

can be chosen as follows:

$$\tilde{\mathbf{F}}' = \frac{e^{im\phi}}{\sqrt{2\pi}} \mathbf{f}'(r, z), \quad (107)$$

where $m = \pm 1/2, \pm 3/2, \dots$, while the eight-element function $\mathbf{f}'(r, z)$:

$$\mathbf{f}' = \left(f_c^{(u)} \ f_c^{(d)} \ f_1^{(u)} \ f_1^{(d)} \ f_2^{(u)} \ f_2^{(d)} \ f_3^{(u)} \ f_3^{(d)} \right)^T, \quad (108)$$

does not depend on ϕ .

The BCs for the valence-band elements of the function $\mathbf{f}'$ on the symmetry axis $r = 0$ are the same as those given in Table I of Subsection II D. The expressions for the conduction-band elements of $\mathbf{f}'$ via the old EF $\mathbf{F}'$:

$$F_c^{(u)} = \frac{e^{i(m-1/2)\phi}}{\sqrt{2\pi}} f_c^{(u)}, \quad F_c^{(d)} = \frac{e^{i(m+1/2)\phi}}{\sqrt{2\pi}} f_c^{(d)}, \quad (109)$$

formally coincide with the relations for the valence-band elements $f_3^{(u)}$ and $f_3^{(d)}$, see Eq. (56), resulting in the same BCs at $r = 0$, which are presented in Table III.

TABLE III. Boundary conditions for the conduction-band elements of $\mathbf{f}'$ at $r = 0$ for different eigenvalues m of the operator of projection of total angular momentum on the symmetry axis.

m	1/2	-1/2	3/2	-3/2	other half-integers
$f_c^{(u)}$	—	0	0	0	0
$\nabla_r f_c^{(u)}$	0	—	—	—	—
$f_c^{(d)}$	0	—	0	0	0
$\nabla_r f_c^{(d)}$	—	0	—	—	—

IV. HOLE STATES IN WURTZITE QUANTUM WIRES

The cylindrical coordinates representation might lead to no practical advantage over the Cartesian one if it were shown that actual nanostructures, such as wurtzite GaN/AlN QDs of pyramidal shape with a hexagonal base⁵¹ or zinc-blende InAs/GaAs square-base pyramidal QDs⁵², could not ever be approximated as cylindrically symmetric. Zinc-blende systems are of special concern here due to the necessity to concede to the cylindrical shape, spherical band and spherical deformation potential approximations, let alone issues⁵³ not taken into account within the classic EF method. On the other hand, one may expect that wurtzite-based systems grown along the [0001] direction are very close to cylindrically symmetric ones due to the cylindrically symmetric band structure, in the quadratic effective-mass approximation including the Kane model, and the geometric shape reasons.

To check this assumption, we present a spectrum of the hole states, as a function of the wavenumber k_z , in an isolated wurtzite GaN QW grown along the [0001] direction that has a regular hexagonal cross-section. The system itself is of interest¹². To calculate the spectrum, we have used the 6×6 valence band Hamiltonian $\mathbf{H}$ in Cartesian coordinates, see Eq. (1). We have also made a cylindrically symmetric shape approximation for the QW, preserving the same cross-sectional area, see Fig. 1, and have calculated the hole spectrum using Eq. (39) in cylindrical coordinates.

We have used the following parameters. The radius of the cylindrical QW is $R = 2$ nm. The same cross-sectional area has a hexagonal QW with the hexagonal side length $L = R\sqrt{2\pi/3\sqrt{3}} \approx 1.100R = 2.2$ nm. The electron band structure parameters of wurtzite GaN used in the computation are⁵⁰: $A_1 = -7.21$, $A_2 = -0.44$, $A_3 = 6.68$, $A_4 = -3.46$, $A_5 = -3.40$, $A_6 = -4.90$. For simplicity, we have neglected the spin-orbit interaction, $\Delta_2 = \Delta_3 = 0$, and also the crystal splitting $\Delta_1 = 0$ for consistency, so that $E_{v1} = E_{v6}$, with the value being used as the zero-energy reference point, and $A_7 = 0$. The upper and the down elements of the function $\mathbf{f}$, see Eq. (39), are then not coupled, and the states are char-




FIG. 1. (Color online) Two studied types of QWs with the same cross-sectional area: (a) hexagonal QW with the hexagon side length L , (b) cylindrical QW with the radius $R = L\sqrt{3}/2$.




FIG. 2. (Color online) Spectra of holes in the hexagonal QW with the side length $L = 2.2$ nm, solid line, and the cylindrical QW with the radius $R = 2$ nm, dot symbols, the latter characterized by the projection l_z of orbital momentum on the z -axis.

acterized by the projection of orbital momentum on the z -axis l_z , with $l_z = m - 1/2$ for the upper spinor elements of $\mathbf{f}$, and $l_z = m + 1/2$ for the down ones.

Due to properties of the space group C_{6v} , all states in the hexagonal QW are either simple or have the two-fold character³¹, not considering the spin degeneracy. The simple states are expected to correspond to the ones that have $l_z = 0$ within the cylindrical QW model. The two-fold degenerate states in the hexagonal QW are then to be related to the states $l_z = \pm n$, for $n = 1, 2, \dots$, in the cylindrical QW. Indeed, as can be seen in Table IV and Fig. 2, the ground and several excited states in QWs of these two geometries not only qualitatively correspond to each other, but are also fairly close in energy. An exception holds for the states with $|l_z| = 3$, which correspond to the simple states in the hexagonal QW.

TABLE IV. Spectrum $E_n^{(h)}$ of several hole states (each doubly spin-degenerate) in a wurtzite GaN QW with the regular hexagonal (side length: 2.2 nm) cross-section and corresponding energies $E^{(c)}$ of hole states in the QW with the circular (radius: 2 nm) cross-section for two values of the wavenumber k_z , presented in Fig. 2. The spectrum $E^{(c)}$ is characterized by the projection l_z of angular momentum on the symmetry axis indicated.

k_z, nm^{-1}	0	1
$E_1^{(h)} (E^{(c)}), \text{meV}$	-24.63 (-24.09 ^a)	-59.48 (-58.49 ^b)
$E_2^{(h)} (E^{(c)}), \text{meV}$	-62.41 (-61.15 ^b)	-59.48 (-58.49 ^b)
$E_3^{(h)} (E^{(c)}), \text{meV}$	-62.41 (-61.15 ^b)	-92.06 (-89.55 ^a)
$E_4^{(h)} (E^{(c)}), \text{meV}$	-72.03 (-69.48 ^a)	-104.9 (-104.17 ^a)
$E_5^{(h)} (E^{(c)}), \text{meV}$	-111.70 (-109.84 ^c)	-111.72 (-109.93 ^c)
$E_6^{(h)} (E^{(c)}), \text{meV}$	-111.70 (-109.84 ^c)	-111.72 (-109.93 ^c)
$E_7^{(h)} (E^{(c)}), \text{meV}$	-120.23 (-117.16 ^b)	-148.82 (-145.22 ^b)
$E_8^{(h)} (E^{(c)}), \text{meV}$	-120.23 (-117.16 ^b)	-148.82 (-145.22 ^b)
$E_9^{(h)} (E^{(c)}), \text{meV}$	-129.04 (-126.9 ^a)	-166.49 (-171.55 ^d)
$E_{10}^{(h)} (E^{(c)}), \text{meV}$	-163.93 (-169.53 ^d)	-182.65 (-171.55 ^d)
$E_{11}^{(h)} (E^{(c)}), \text{meV}$	-181.17 (-169.53 ^d)	-194.11 (-192.58 ^c)
$E_{12}^{(h)} (E^{(c)}), \text{meV}$	-191.58 ^e (-186.89 ^c)	-194.11 (-192.58 ^c)

^a $l_z = 0$.

^b $|l_z| = 1$.

^c $|l_z| = 2$.

^d $|l_z| = 3$.

^e Degenerate with the $E_{13}^{(h)}$ level.

V. CONCLUSIONS

Having composed “cylindrical” combinations of the Brillouin zone center Bloch functions to be used as new basis functions, we have made a cylindrical coordinate transformation of 6×6 valence-band and 8×8 Kane Hamiltonians for wurtzite and zinc-blende semiconductor heterostructures. As a result, for cylindrically symmetric structures (using the spherical band approximation for zinc-blende), we have guaranteed that the EFs themselves are eigenstates of the operator of projection of total angular momentum on the symmetry axis, while the effective Hamiltonians parametrically depend on an eigenvalue $m = \pm 1/2, \pm 3/2, \dots$ of the operator. In the Hamiltonians, we have taken into account the deformation effects and have made an allowance for an external magnetic field applied along the symmetry axis. The advantage of the presented method over the one developed by Vahala and Sercel^{32,33} is the formulation of a universal Hamiltonian (for each specific case, wurtzite or zinc-blende, 6×6 or 8×8 model), valid for any half-integer m .

The results have been applied to the problem of hole states in an isolated wurtzite GaN QW grown along the [0001] direction with a regular hexagonal cross-section. Making the cylindrically symmetric shape approximation for this QW, we have shown a fairly good correspondence of the spectrum in the cylindrical QW to that in the

hexagonal one.

ACKNOWLEDGMENTS

This work was supported by the NSERC and CRC Program, Canada.

- ¹E. Borovitskaya and M.E. Shur, in *Quantum Dots*, Selected Topics in Electronics and Systems Vol. **25**, edited by E. Borovitskaya and M.E. Shur (World Scientific, Singapore, 2002), p. 1.
- ²E. Kapon, in *Quantum Well Lasers*, edited by in: P.S. Zory, Jr. (Academic Press, New York, 1993), p. 461.
- ³P.M. Petroff, A. Lorke, and A. Imamoglu, *Physics Today* **54**, 46 (2001).
- ⁴M.S. Gudiksen, L.J. Lauhon, J. Wang, D.C. Smith, and C.M. Lieber, *Nature (London)* **415**, 617 (2002).
- ⁵P.O. Anikeeva, J.E. Halpert, M.G. Bawendi, and V. Bulović, *Nano Letters* **9** 2532 (2009).
- ⁶J.A. Brum and P. Hawrylak, *Superlattices Microstruct.* **22**, 431 (1997).
- ⁷D. Loss and D.P. DiVincenzo, *Phys. Rev. A* **57**, 120 (1998).
- ⁸J.M. Elzerman, R. Hanson, L.H.W. van Beveren, S. Tarucha, L.M.K. Vandersypen, and L.P. Kouwenhoven, in *Quantum Dots: A Doorway to Nanoscale Physics*, Lecture Notes in Physics Vol. **667**, edited by W.D. Heiss (Springer, Berlin, 2005), p. 25.
- ⁹B.D. Gerardot, D. Brunner, P.A. Dalgarno, P. Öhberg, S. Seidl, M. Kroner, K. Karrai, N.G. Stoltz, P.M. Petroff, and R.J. Warburton, *Nature (London)* **451**, 441 (2008).
- ¹⁰H. Fu, L.-W. Wang, and A. Zunger, *Phys. Rev. B* **57**, 9971 (1998).
- ¹¹A. Di Carlo, *Semicond. Sci. Technol.* **18** R1 (2003).
- ¹²M.P. Persson and A. Di Carlo, *J. Appl. Phys.* **104**, 073718 (2008).
- ¹³D. Mourad, S. Barthel, and G. Czycholl, *Phys. Rev. B* **81**, 165316 (2010).
- ¹⁴F. Long, W.E. Hagston, P. Harrison, T. Stirner, *J. Appl. Phys.* **82**, 3414 (1997).
- ¹⁵A. Zunger, *phys. stat. sol. (a)* **190**, 467 (2002).
- ¹⁶Y. Fu, M. Willander, E.L. Ivchenko, and A.A. Kiselev, *Phys. Rev. B* **47**, 13498 (1993).
- ¹⁷O. Krebs and P. Voisin, *Phys. Rev. Lett.* **77**, 1829 (1996).
- ¹⁸E.L. Ivchenko, A.Yu. Kaminski, and U. Rössler, *Phys. Rev. B* **54**, 5852 (1996).
- ¹⁹E.E. Takhtamirov and V.A. Volkov, *JETP* **89**, 1000 (1999).
- ²⁰E.E. Takhtamirov and V.A. Volkov, *JETP* **90**, 1063 (2000).
- ²¹E.E. Takhtamirov and V.A. Volkov, *JETP Lett.* **71** 422 (2000).
- ²²J.M. Luttinger and W. Kohn, *Phys. Rev.* **97**, 869 (1955).
- ²³J.M. Luttinger, *Phys. Rev.* **102**, 1030 (1956).
- ²⁴L. Leibler, *Phys. Rev. B* **12**, 4443 (1975).
- ²⁵A. Zunger, *phys. stat. sol. (b)* **224**, 727 (2001).
- ²⁶O. Marquardt, D. Mourad, S. Schulz, T. Hickel, G. Czycholl, and J. Neugebauer, *Phys. Rev. B* **78**, 235302 (2008).
- ²⁷M. Grundmann, O. Stier, and D. Bimberg, *Phys. Rev. B* **52**, 11969 (1995).
- ²⁸O. Stier, M. Grundmann, and D. Bimberg, *Phys. Rev. B* **59**, 5688 (1999).
- ²⁹A.D. Andreev and E.P. O'Reilly, *Phys. Rev. B* **62**, 15851 (2000).
- ³⁰A. Messiah, *Quantum Mechanics* (North-Holland, Amsterdam, 1961), Vol. I.
- ³¹L.D. Landau and E.M. Lifshitz, *Quantum Mechanics: Non-relativistic Theory*, 3rd ed. (Pergamon Press, Oxford, 1991).
- ³²K.J. Vahala and P.C. Sercel, *Phys. Rev. Lett.* **65**, 239 (1990).
- ³³P.C. Sercel and K.J. Vahala, *Phys. Rev. B* **42**, 3690 (1990).
- ³⁴D. Schechter, *J. Phys. Chem. Solids* **23**, 237 (1962).
- ³⁵A. Baldereschi and N.O. Lipari, *Phys. Rev. B* **8**, 2697 (1973).
- ³⁶L.C. Lew Yan Voon, C. Galeriu, B. Lassen, M. Willatzen, and R. Melnik, *Appl. Phys. Lett.* **87**, 041906 (2005).
- ³⁷Work in progress.
- ³⁸G.L. Bir and G.E. Pikus, *Symmetry and Strain-Induced Effects in Semiconductors*, (Wiley, New York, 1974).
- ³⁹S.L. Chuang and C.S. Chang, *Phys. Rev. B* **54**, 2491 (1996).
- ⁴⁰Yu.M. Sirenko, J.-B. Jeon, K.W. Kim, M.A. Littlejohn, and M.A. Stroschio, *Phys. Rev. B* **53**, 1997 (1996).
- ⁴¹G.B. Ren, Y.M. Liu, and P. Blood, *Appl. Phys. Lett.* **74**, 1117 (1999).
- ⁴²L.D. Landau and E.M. Lifshitz, *Theory of Elasticity*, 2nd ed. (Pergamon Press, Oxford, 1970).
- ⁴³E.E. Takhtamirov and V.A. Volkov, *Semicond. Sci. Technol.* **12**, 77 (1997).
- ⁴⁴E.O. Kane, *J. Phys. Chem. Solids*, **1**, 249 (1957).
- ⁴⁵P.-O. Löwdin, *J. Chem. Phys.* **19**, 1396 (1951).
- ⁴⁶P. Rinke, M. Winkelkemper, A. Qteish, D. Bimberg, J. Neugebauer, and M. Scheffler, *Phys. Rev. B* **77**, 075202 (2008).
- ⁴⁷J.Y. Fu and M.W. Wu, *J. Appl. Phys.* **104**, 093712 (2008).
- ⁴⁸T.B. Bahder, *Phys. Rev. B* **41**, 11992 (1990).
- ⁴⁹T.B. Bahder, *Phys. Rev. B* **46**, 9913 (1992).
- ⁵⁰I. Vurgaftman, J.R. Meyer, and L.R. Ram-Mohan, *J. Appl. Phys.* **89**, 5815 (2001).
- ⁵¹M. Arley, J.L. Rouvière, F. Widmann, B. Daudin, G. Feuillet, and H. Mariette, *Appl. Phys. Lett.* **74**, 3287 (1999).
- ⁵²D.M. Bruls, J.W.A.M. Vugs, P.M. Koenraad, H.W.M. Salemink, J.H. Wolter, M. Hopkinson, M.S. Skolnick, Fei Long, and S.P.A. Gill, *Appl. Phys. Lett.* **81**, 1708 (2002).
- ⁵³G. Bester and A. Zunger, *Phys. Rev. B* **71**, 045318 (2005).